

HAIPLEN H30 T4 HT

Polypropylene Homopolymer

Taro Plast S.p.A.

Message:

Polypropylene homopolymer talcum filled 20%. heat stabilized
Available: all colors, UV stabilized (L), anti-static (AS).

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	Antistatic		
	Heat Stabilizer		
	UV Stabilizer		
Features	Antistatic		
	Good UV Resistance		
	Heat Stabilized		
	Homopolymer		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	1.1	%	
Across Flow	1.1	%	
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	40	%	ASTM D638, ISO 527-2
Flexural Modulus	2500	MPa	ASTM D790, ISO 178
Flexural Strength	50.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	30	J/m	ISO 180, ASTM D256
Aging	Nominal Value	Unit	
Heat Aging - Resistance ¹	150	°C	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	75.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature			

--	155	°C	ASTM D1525, ISO 306/A 3 ²
--	85.0	°C	ASTM D1525, ISO 306/B 4 ³
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	190 to 220	°C	
Mold Temperature	30.0 to 50.0	°C	
Injection Rate	Moderate		
NOTE			
1.	700 hrs		
2.	Loading 1 (10 N)		
3.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

