# Yuyao PET PETG30

### Polyethylene Terephthalate

Yuyao Tenglong Plastics Co., Ltd.

#### Message:

Yuyao PET PETG30 is a Polyethylene Terephthalate (PET) product filled with 30% glass fiber. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PET PETG30 include electrical/electronic applications, automotive, engineering/industrial parts and lighting applications.

Characteristics include:

Flame Retardant

Creep Resistant

Fatigue Resistant

Good Dimensional Stability

Good Processability

General Information					
Filler / Reinforcement	Glass Fiber,30% Filler by Weig	Glass Fiber,30% Filler by Weight			
Additive	Flame Retardant				
Features	Fatigue Resistant				
	Flame Retardant				
	Good Creep Resistance				
	Good Dimensional Stability				
	Good Impact Resistance				
	Good Processability				
	High Heat Resistance				
Uses	Automotive Applications				
	Automotive Under the Hood				
	Connectors				
	Electrical Parts				
	Lighting Fixtures				
	Printed Circuit Boards				
	Valves/Valve Parts				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.45	g/cm³	ASTM D792		
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength	120	МРа	ASTM D638		
Tensile Elongation (Break)	3.0	%	ASTM D638		
Flexural Modulus	7500	МРа	ASTM D790		
Flexural Strength	180	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		

Notched Izod Impact (Area)	11.0	kJ/m²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (	(1.8		
MPa, Unannealed)	230	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	115 to 120	°C	
Drying Time	6.0 to 8.0	hr	
Processing (Melt) Temp	240 to 265	°C	
Mold Temperature	60.0 to 100	°C	
Injection Pressure	70.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

