

# InnoPlus HD3000C

High Density Polyethylene

PTT Global Chemical Public Company Limited

## Message:

InnoPlus HD3000C and HD3001C are high density polyethylene which are specially designed for beverage caps. Both grades have excellent organoleptic properties which prevent unpleasant odor and taste from cap or closure to transfer to water. They show good processability in either injection molding or compression molding machine.

### Additive:

InnoPlus HD3000C with slip agent.

InnoPlus HD3001C without slip agent.

Typical Application: Beverage caps for mineral, stiller, sparkling water and carbonated soft drink.

General Information			
Additive	Slip		
Features	Food Contact Acceptable		
	Good Organoleptic Properties		
	Good Processability		
	Low Odor Transfer		
	Low Taste Transfer		
	Slip		
Uses	Caps		
	Closures		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Compression Molding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (25% Igepal, F50)	24.0	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	25.5	MPa	
Break	31.4	MPa	
Tensile Elongation (Break)	800	%	ASTM D638
Apparent Bending Modulus	775	MPa	ASTM D747

Flexural Modulus	1110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>1</sup>	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	122	°C	ASTM D1525 <sup>2</sup>
Peak Melting Temperature	130	°C	ASTM D3418
Additional Information	Nominal Value	Unit	
Compression Molding Temperature	160 to 180	°C	
Injection	Nominal Value	Unit	
Rear Temperature	170 to 200	°C	
Middle Temperature	170 to 200	°C	
Front Temperature	170 to 200	°C	
NOTE			
1.	Partial Break		
2.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

