

Innothane® IE-3010

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

IE-3010 is a fast setting 70 shore D polyurethane formulated for room temperature hand-batch processing and meter mix equipment. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA or TDI. It has excellent green strength for good demold characteristics.

General Information			
Features	Good Green Strength Good Mold Release		
RoHS Compliance	RoHS Compliant		
Appearance	White		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Cured	1.06	g/cm ³	
Hardener	1.06	g/cm ³	
Base Resin	1.16	g/cm ³	
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D2566
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1210	MPa	ASTM D790
Flexural Strength	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	72.0	°C	
1.8 MPa, Unannealed	65.0	°C	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 100		
Hardener	Mix Ratio by Weight: 92 Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 100		
Demold Time	5.0 to 15	min	

Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
25°C ¹	0.075	Pa·s	
25°C ²	0.15	Pa·s	
25°C ³	0.45	Pa·s	
Curing Time (25°C)	1.7E+2	hr	
Gel Time	0.33 to 0.67	min	

Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	65 to 75		ASTM D2240
Tensile Modulus	1140	MPa	ASTM D638
Tensile Strength	34.1	MPa	ASTM D638
Tensile Elongation at Break	24	%	ASTM D638

NOTE

1. Resin
2. Mixed
3. Hardener

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT