

megol® P21 A60X3

Styrene Ethylene Butylene Styrene Block Copolymer

API SpA

Message:

megol® P21 A60X3 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by injection molding and is available in Europe.

Characteristics include:

Chemical Resistant

Antistatic

Eco-Friendly/Green

Fast Molding Cycle

Good Processability

General Information			
Additive	Antistatic		
Features	Acid Resistant		
	Antistatic		
	Base Resistant		
	Detergent Resistant		
	Fast Molding Cycle		
	Good Chemical Resistance		
	Good Processability		
	Good UV Resistance		
	Good Weather Resistance		
	High Heat Resistance		
	Low Temperature Resistant		
	Ozone Resistant		
	Recyclable Material		
Agency Ratings	DIN EN 100 015/1		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	5.80	MPa	
100% Strain	2.90	MPa	
300% Strain	4.00	MPa	
Tensile Elongation (Break)	720	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method


Tear Strength ¹	27.0	kN/m	ASTM D624
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+7	ohms	ASTM D257
Additional Information	Nominal Value		
Ozone Resistance ² (40°C)	Excellent		
NOTE			
1.	Without Notch		
2.	72 hr, 200 ppcm, Tension=20%		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT