

LEXAN™ 153R resin

Polycarbonate

SABIC Innovative Plastics

Message:

Nonhalogenated. 2.5 MFR. Blowmolding/extrusion. UV-stabilized. Internal mold release.

General Information			
UL YellowCard	E121562-220869		
Additive	demoulding		
	UV stabilizer		
Features	Halogen-free		
Processing Method	Extrusion blow molding		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
--	1.20	g/cm ³	ASTM D792
--	1.19	g/cm ³	ASTM D792
Specific Volume	0.835	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	2.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ASTM D570
24 hr	0.15	%	ASTM D570
Equilibrium, 23°C	0.35	%	ASTM D570
Equilibrium, 100°C	0.58	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	70		ASTM D785
Class r	118		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	62.1	MPa	ASTM D638
Fracture	65.5	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	7.0	%	ASTM D638
Fracture	110	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	2340	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	93.1	MPa	ASTM D790

Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	10.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	750	J/m	ASTM D256
Unnotched Izod Impact (23°C)	3200	J/m	ASTM D4812
Dart Drop Impact (23°C)	169	J	ASTM D3029
Tensile Impact Strength ⁵	630	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	138	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	132	°C	ASTM D648
Vicat Softening Temperature	157	°C	ASTM D1525 ⁶
CLTE - Flow (-40 to 95°C)	6.8E-5	cm/cm/°C	ASTM E831
Specific Heat	1260	J/kg/°C	ASTM C351
Thermal Conductivity	0.19	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms · cm	ASTM D257
Dielectric Strength (3.20 mm, in Air)	15	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
50 Hz	3.17		ASTM D150
60 Hz	3.17		ASTM D150
1 MHz	2.96		ASTM D150
Dissipation Factor			ASTM D150
50 Hz	9.0E-4		ASTM D150
60 Hz	9.0E-4		ASTM D150
1 MHz	0.010		ASTM D150
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance (2540 µm)	88.0	%	ASTM D1003
Haze (2540 µm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	299 - 321	°C	
Middle Temperature	310 - 332	°C	
Front Temperature	321 - 343	°C	
Nozzle Temperature	316 - 338	°C	
Processing (Melt) Temp	321 - 343	°C	
Mold Temperature	82.2 - 116	°C	

Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm
Extrusion	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.020	%
Cylinder Zone 1 Temp.	260 - 291	°C
Cylinder Zone 2 Temp.	260 - 291	°C
Cylinder Zone 3 Temp.	260 - 291	°C
Cylinder Zone 4 Temp.	260 - 291	°C
Cylinder Zone 5 Temp.	260 - 291	°C
Adapter Temperature	260 - 291	°C

Extrusion instructions

Melt Temperature (Parison): 266 - 279 °C Minimum Moisture Content: 0.01 % Mold Temperature: 60 - 99 °C

NOTE

- | | |
|----|---------------------------|
| 1. | Type 1, 50mm/min |
| 2. | Type 1, 50mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |
| 5. | Type S |
| 6. | 标准 B (120°C/h), 载荷2 (50N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT