

SLOVAMID® 6 FRC 2 LI

Polyamide 6

Plastcom

Message:

Determined for electrotechnical use. Delivered in natural mode. PA 6 for injection moulding with reduced flammability, with nonhalogen flame retardant. Excellent fluidity of the material predetermines it for the manufacturing of complicated small and large surface mouldings. Possible use for products with wall thickness from 0.5 mm. High grade brightness also at coloured types. Delivered in the full RAL colour scale.

General Information			
Additive	Flame Retardant		
	Impact Modifier		
Features	Flame Retardant		
	Halogen Free		
	High Gloss		
	Impact Modified		
	Medium Rigidity		
Uses	Electrical/Electronic Applications		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PA 6		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	1.2	%	
Flow	1.5	%	
Water Content	0.15	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Stress (Yield)	70.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	3.0	kJ/m ²	

23°C	7.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	110	kJ/m ²	
23°C	120	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	60.0	°C	ISO 75-2/B
Vicat Softening Temperature	200	°C	ISO 306/B
Melting Temperature (DSC)	220	°C	ISO 3146
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	50.0 to 70.0	°C	
Injection Pressure	70.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT