

Starflam RF0077P

Polyamide 66/6 Copolymer
Eurostar Engineering Plastics

Message:

RFOO77P is a Halogen Free and Red Phosphorous Free Flame Retardant, Glass Fiber Reinforced, PA66 / PA6 Injection Molding Resin (also known as RF1007Z270EM)

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	Low (to None) Phosphorus Content		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183
Molding Shrinkage - Flow (24 hr)	0.10 to 0.30	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11500	MPa	ISO 527-2/1
Tensile Stress (Break)	150	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	10500	MPa	ISO 178
Flexural Stress	215	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ¹ (23°C)	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ² (23°C)	60	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed, 64.0 mm Span)	220	°C	ISO 75-2/Af
Ball Pressure Test ⁴ (210°C)	Pass		IEC 60695-10-2
RTI Elec	140	°C	UL 746
RTI Imp	110	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
High Amp Arc Ignition (HAI)	PLC 0		UL 746
Hot-wire Ignition (HWI)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94

Glow Wire Flammability Index (0.800 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	775	°C	
1.50 mm	775	°C	
3.00 mm	825	°C	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	265 to 275	°C	
Middle Temperature	265 to 275	°C	
Front Temperature	265 to 280	°C	
Processing (Melt) Temp	270 to 280	°C	
Mold Temperature	60.0 to 100	°C	
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4		
4.	Approximate maximum		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT