

Medalist® MD-300

Thermoplastic Elastomer

Teknor Apex Company

Message:

This compound is designed for overmold to polycarbonate (PC), ABS and blends of PC and ABS.

General Information			
Uses	Drug		
	Medical/nursing supplies		
Agency Ratings	ISO 10993 Part 5		
Appearance	Translucent		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	2.6	%	ASTM D955
Transverse flow	1.9	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	30		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	1.00	MPa	ASTM D412
200% strain	1.62	MPa	ASTM D412
300% strain	2.34	MPa	ASTM D412
Tensile Strength (Break)	3.31	MPa	ASTM D412
Tensile Elongation (Break)	530	%	ASTM D412
Tear Strength	20.1	kN/m	ASTM D624
Compression Set (23°C, 22 hr)	38	%	ASTM D395
Additional Information	Nominal Value		
Adhesion to ABS			
Adhesion to PC			
Adhesion to PC/ABS			
Injection	Nominal Value	Unit	
Drying Temperature	60.0	°C	

Drying Time	2.0 - 4.0	hr
Rear Temperature	127 - 149	°C
Middle Temperature	138 - 160	°C
Front Temperature	149 - 171	°C
Nozzle Temperature	171 - 193	°C
Processing (Melt) Temp	171 - 193	°C
Mold Temperature	21.1 - 37.8	°C
Injection Pressure	1.38 - 5.52	MPa
Back Pressure	0.172 - 0.689	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Moisture can degrade the material. Drying is suggested. This can be accomplished by placing the material in a desiccant dryer for 2 to 4 hours at 140°F.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	138 - 149	°C
Cylinder Zone 2 Temp.	149 - 160	°C
Cylinder Zone 3 Temp.	160 - 182	°C
Cylinder Zone 5 Temp.	171 - 193	°C
Die Temperature	182 - 204	°C

Extrusion instructions

螺杆转速30 - 100 rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT