

TYNELOY® NA4300

Polyphenylene Ether + PS

Tyne Plastics LLC.

Message:

TYNELOY® NA4300 is a Polyphenylene Ether + PS (PPE+PS) material filled with 30% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	117	MPa	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	131	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	154	°C	
1.8 MPa, Unannealed	149	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT