

# Ecomass® 4703ZB92

Thermoplastic Polyurethane Elastomer

Ecomass Technologies

## Message:

Ecomass® 4703ZB92 is a Thermoplastic Polyurethane Elastomer material filled with filler. It is available in North America for injection molding. Primary attribute of Ecomass® 4703ZB92: Non-Toxic.

General Information			
Filler / Reinforcement	Filler		
Features	Non-Toxic		
	Radiaton Shielding		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	6.88	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	669	MPa	ASTM D638
Tensile Strength	11.0	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	448	MPa	ASTM D790
Flexural Strength	20.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	160	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 93.3	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	204 to 221	°C	
Mold Temperature	10.0 to 26.7	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT