

LNP™ KONDUIT™ OX11315 compound

Polyphenylene Sulfide

SABIC Innovative Plastics Asia Pacific

Message:

LNP* KONDUIT* OX11315 is a thermally conductive, electrically insulative, mineral filled PPS Flame Retardant compound.

Also known as: LNP* KONDUIT* Compound OX11315

Product Reorder name: OX11315

General Information			
UL YellowCard	E207780-101069096		
Filler / Reinforcement	Mineral		
Features	Electrically Insulating		
	Flame Retardant		
	Thermally Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
--	1.78	g/cm ³	
--	1.76	g/cm ³	
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.34	%	
Across Flow : 24 hr	0.44	%	
Water Absorption			
24 hr, 50% RH	0.010	%	ASTM D570
Equilibrium, 23°C, 50% RH	< 0.010	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	30100	MPa	ASTM D638
--	18400	MPa	ISO 527-2/1
Tensile Strength			
Break ²	41.0	MPa	ASTM D638
Break	54.0	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	0.20	%	ASTM D638
Break	0.30	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	26500	MPa	ASTM D790
-- ⁵	21400	MPa	ISO 178
Flexural Stress			
--	84.0	MPa	ISO 178

Break, 50.0 mm Span ⁶	82.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	16	J/m	ASTM D256
23°C ⁷	1.7	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	54	J/m	ASTM D4812
23°C ⁸	3.9	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	5.14	J	ASTM D3763
--	1.14	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	275	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁹	275	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	242	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁰	238	°C	ISO 75-2/Af
Specific Heat	1260	J/kg/°C	ASTM C351
Thermal Conductivity			ASTM E1461
-- ¹¹	3.5	W/m/K	
-- ¹²	15	W/m/K	
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.4E+15	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.00 mm	V-0		
2.50 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Shot Size	50 to 75	%	
Rear Temperature	316 to 343	°C	
Middle Temperature	316 to 343	°C	
Front Temperature	316 to 343	°C	
Processing (Melt) Temp	321 to 349	°C	
Mold Temperature	110 to 150	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			

1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	1.3 mm/min
5.	2.0 mm/min
6.	1.3 mm/min
7.	80*10*4
8.	80*10*4
9.	80*10*4 mm
10.	80*10*4 mm
11.	through-plane, 10*10*3mm sample
12.	in-plane, ø25*0.4mm disc

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

