

Braskem PP FT120W2

Polypropylene Homopolymer

Braskem America Inc.

Message:

Description
Antistatic, Good Mold Release
Applications
Suggested Uses Include Closures, Housewares

General Information			
Additive	Antistatic		
Features	Antistatic		
	Food Contact Acceptable		
	Good Mold Release		
	Homopolymer		
Uses	Closures		
	Household Goods		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	37.2	MPa	ASTM D638
Tensile Elongation ² (Yield)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant ³	1590	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256A
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

