

# Next Nylon 66 Prime Series PG30-01RD

Polyamide 66

Next Polymers Ltd.

## Message:

Description

PA66 Glass Fiber Reinforced Red Compound

Product Applications

Generally used in all sector of industries such as Thermoset component, inlet & outlet pipes, valve bodies relay parts, engine mounts etc

Benefits

offering Excellent combination of thermal and Mechanical properties.

| General Information        |      |                                                       |                   |             |
|----------------------------|------|-------------------------------------------------------|-------------------|-------------|
| Filler / Reinforcement     |      | Glass fiber reinforced material, 30% filler by weight |                   |             |
| Uses                       |      | Valve/valve components<br>Piping system               |                   |             |
| Agency Ratings             |      | EC 1907/2006 (REACH)                                  |                   |             |
| RoHS Compliance            |      | RoHS compliance                                       |                   |             |
| Appearance                 |      | Red                                                   |                   |             |
| Processing Method          |      | Injection molding                                     |                   |             |
| Physical                   | Dry  | Conditioned                                           | Unit              | Test Method |
| Specific Gravity           | 1.36 | --                                                    | g/cm <sup>3</sup> | ASTM D792   |
| Molding Shrinkage          |      |                                                       |                   | ASTM D955   |
| Flow                       | 0.24 | --                                                    | %                 | ASTM D955   |
| Transverse flow            | 0.49 | --                                                    | %                 | ASTM D955   |
| Water Absorption           |      |                                                       |                   | ASTM D570   |
| 23°C, 24 hr                | 1.8  | --                                                    | %                 | ASTM D570   |
| Saturation <sup>1</sup>    | 6.1  | --                                                    | %                 | ASTM D570   |
| Hardness                   | Dry  | Conditioned                                           | Unit              | Test Method |
| Rockwell Hardness          |      |                                                       |                   | ASTM D785   |
| Class m                    | 110  | --                                                    |                   | ASTM D785   |
| Class r                    | 120  | --                                                    |                   | ASTM D785   |
| Mechanical                 | Dry  | Conditioned                                           | Unit              | Test Method |
| Tensile Strength           | 175  | 125                                                   | MPa               | ASTM D638   |
| Tensile Elongation (Break) | 4.0  | 6.0                                                   | %                 | ASTM D638   |
| Flexural Modulus           | 9200 | 6200                                                  | MPa               | ASTM D790   |
| Flexural Strength          | 255  | 190                                                   | MPa               | ASTM D790   |
| Impact                     | Dry  | Conditioned                                           | Unit              | Test Method |
| Notched Izod Impact (23°C) | 120  | 130                                                   | J/m               | ASTM D256   |
| Thermal                    | Dry  | Conditioned                                           | Unit              | Test Method |

|                                   |         |             |         |             |
|-----------------------------------|---------|-------------|---------|-------------|
| Deflection Temperature Under Load |         |             |         | ASTM D648   |
| 0.45 MPa, not annealed            | 260     | --          | °C      | ASTM D648   |
| 1.8 MPa, not annealed             | 254     | --          | °C      | ASTM D648   |
| Melting Temperature               | 262     | --          | °C      | ASTM D2117  |
| Electrical                        | Dry     | Conditioned | Unit    | Test Method |
| Surface Resistivity               | 1.0E+13 | --          | ohms    | IEC 60093   |
| Volume Resistivity                | 1.0E+16 | 1.0E+16     | ohms·cm | IEC 60093   |
| Dielectric Strength               | 28      | 24          | kV/mm   | IEC 60243-1 |
| Comparative Tracking Index        | 600     | --          | V       | IEC 60112   |
| Flammability                      | Dry     | Conditioned | Unit    | Test Method |
| Flame Rating (0.800 mm)           | HB      | --          |         | UL 94       |
| Additional Information            |         |             |         |             |

干燥

This grade is not suitable for food contact, medical devices or toy applications

|                                    |             |      |  |
|------------------------------------|-------------|------|--|
| Injection                          | Dry         | Unit |  |
| Drying Temperature - Hot Air Dryer | 80.0        | °C   |  |
| Drying Time                        | 4.0 - 6.0   | hr   |  |
| Suggested Max Moisture             | 0.20        | %    |  |
| Rear Temperature                   | 270 - 280   | °C   |  |
| Middle Temperature                 | 280 - 290   | °C   |  |
| Front Temperature                  | 290 - 300   | °C   |  |
| Mold Temperature                   | 65.0 - 85.0 | °C   |  |

#### NOTE

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT