

PRIMALLOY® B1900

Thermoplastic Elastomer

Mitsubishi Chemical Performance Polymers, Inc.

Message:

PRIMALLOY® B1900 is a Thermoplastic Elastomer (TPE) material. It is available in Asia Pacific, Europe, or North America. Primary attribute of PRIMALLOY® B1900: Flame Rated.

General Information			
UL YellowCard	E117009-220014		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min	ISO 1133
Molding Shrinkage ¹			Internal Method
Across Flow : 2.00 mm	0.70	%	
Flow : 2.00 mm	0.90	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	36		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	27.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	1000	%	ISO 527-2
Flexural Modulus	85.0	MPa	ISO 178
Flexural Stress	4.50	MPa	ISO 178
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	110	kN/m	ISO 34-1
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	135	°C	JIS K7206 ²
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
NOTE			
1.	120x120x2 mm test plaque		
2.	50°C/h, A (10N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

