

OmniPro™ CPP GRC50

Polypropylene Copolymer

OMNI Plastics, LLC

Message:

50% Glass Reinforced, Chemically Coupled, Copolymer Polypropylene

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	Chemically Coupled		
UL File Number	E138590		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	88.3	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength	134	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	152	°C	
1.8 MPa, Unannealed, 3.18 mm	138	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Rear Temperature	204 to 249	°C	
Middle Temperature	216 to 260	°C	
Front Temperature	216 to 260	°C	
Nozzle Temperature	216 to 260	°C	
Processing (Melt) Temp	216 to 260	°C	
Mold Temperature	26.7 to 60.0	°C	
Back Pressure	0.345 to 0.689	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT