

Baynat® 0759 BX Isocyanate

Polyurethane (MDI)

Covestro - PUR

Message:

Baynat 0759 BX Isocyanate is a low to medium functionality polymeric diphenylmethane diisocyanate (PMDI) with a moderately high 2,4 -MDI isomer content.

General Information		
Appearance	Brown	
Forms	Liquid	
Processing Method	Foam Processing	
Physical	Nominal Value	Unit
Specific Gravity ¹	1.22	g/cm ³
Viscosity (25°C)	20 to 50	mPa·s
Flash Point - PMCC	> 200	°C
NCO	31.8 to 32.8	wt%
NOTE		
1.	25°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

