

TECHNYL® A 216 V30 NATURAL

Polyamide 66
Solvay Engineering Plastics

Message:
Polyamide PA66, reinforced with 30% of glass fibre, for injection moulding.

General Information				
UL YellowCard		E44716-235561		
Uses		Automotive Applications		
Appearance		Black		
		Colors Available		
		Natural Color		
Processing Method		Injection Molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)		>PA66-GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	0.80	--	%	
Flow	0.50	--	%	
Water Absorption (23°C, 24 hr)	0.80	--	%	ISO 62
Molding Shrinkage Isotropy	0.620	--		Internal Method
Fire and Smoke F Index - I2, F3	2	--		NF F16-101
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	7500	MPa	ISO 527-2/1A
Tensile Stress (Break)	190	135	MPa	ISO 527-2/1A
Tensile Strain (Break)	3.0	4.0	%	ISO 527-2/1A
Flexural Modulus	8400	5900	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	12	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	80	95	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	11	16	kJ/m ²	ISO 180/1A

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	255	--	°C	ISO 75-2/Af
Melting Temperature	263	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	2.5E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	6.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	2.0E+13	ohms·cm	IEC 60093
Electric Strength	40	30	kV/mm	IEC 60243-1
Relative Permittivity	3.75	4.00		IEC 60250
Dissipation Factor	0.010	0.11		IEC 60250
Comparative Tracking Index				IEC 60112
Solution A	600	600	V	
Solution B	500	500	V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
1.60 mm	650	--	°C	
3.20 mm	750	--	°C	
Glow Wire Ignition Temperature (1.60 mm)	650	--	°C	IEC 60695-2-13
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	260 to 270		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	60.0 to 80.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT