

Medalist® MD-84383 (PRELIMINARY DATA)

Thermoplastic Elastomer

Teknor Apex Company

Message:

Medalist™MD-8451 is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is extrusion or injection molding. Medalist™The main characteristics of the MD-8451 are: flame retardant/rated flame.

Typical application areas include:

- medical/health care
- safety equipment

General Information			
Uses	Safety equipment		
	Drug		
	Medical/nursing supplies		
Appearance	Opacity		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.998	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	17	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	82		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	16.5	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	105	°C	UL 1581
Brittleness Temperature	< -60.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
23°C	2.3E+16	ohms · cm	ASTM D257
50°C	3.3E+15	ohms · cm	ASTM D257
Dielectric Strength	58	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	2.27		ASTM D150
1 MHz	2.27		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	4.5E-3		ASTM D150

1 MHz	5.8E-3	ASTM D150	
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Oxygen Index	18	%	ASTM D2863
Additional Information			
Maximum Continuous Operating Temperature, UL-1581: 105C rated; Meets 720 hour Sunlight Resistance			
Injection	Nominal Value	Unit	
Rear Temperature	199 - 216	°C	
Middle Temperature	213 - 221	°C	
Front Temperature	221 - 227	°C	
Nozzle Temperature	221 - 229	°C	
Processing (Melt) Temp	221 - 229	°C	
Mold Temperature	25.0 - 65.6	°C	
Injection Pressure	1.38 - 6.89	MPa	
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	50 - 100	rpm	
Cushion	3.81 - 25.4	mm	
Injection instructions			
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	193 - 210	°C	
Cylinder Zone 2 Temp.	199 - 216	°C	
Cylinder Zone 3 Temp.	213 - 221	°C	
Cylinder Zone 5 Temp.	221 - 227	°C	
Die Temperature	221 - 229	°C	
Extrusion instructions			
Screw Speed: 30 to 100 rpm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT