## POLYCOMPO PE 5000SR

High Density Polyethylene POLYCOMPO Co.,Ltd.

## Message:

POLYCOMPO PE 5000SR is a High Density Polyethylene product. It can be processed by extrusion and is available in Asia Pacific. Typical application: Adhesives/Tapes.

| General Information                      |               |          |                      |
|--|---------------|----------|----------------------|
| Features                                 | Good Strength |          |                      |
| Uses                                     | Netting       |          |                      |
|  | Tape          |          |                      |
|  |               |          |                      |
| Forms                                    | Pellets       |          |                      |
| Processing Method                        | Extrusion     |          |                      |
| Physical                                 | Nominal Value | Unit     | Test Method          |
| Density                                  | 0.955         | g/cm³    | ISO 1183             |
| Melt Mass-Flow Rate (MFR)                | 0.37          | g/10 min | ISO 1133             |
| Environmental Stress-Cracking Resistance |               |          |                      |
| (Compression Molded)                     | 150           | hr       | ASTM D1693           |
| Hardness                                 | Nominal Value | Unit     | Test Method          |
| Durometer Hardness (Shore D,             |               |          |                      |
| Compression Molded)                      | 64            |          | ASTM D2240, ISO 868  |
| Mechanical                               | Nominal Value | Unit     | Test Method          |
| Tensile Stress                           |               |          | ISO 527-2            |
| Yield, Compression Molded                | 26.0          | MPa      |                      |
| Break, Compression Molded                | 17.0          | MPa      |                      |
| Tensile Strain (Break, Compression       |               |          |                      |
| Molded)                                  | 500           | %        | ISO 527-2            |
| Flexural Modulus (Compression Molded)    | 1100          | MPa      | ISO 178              |
| Impact                                   | Nominal Value | Unit     | Test Method          |
| Charpy Notched Impact Strength           | 12            | kJ/m²    | ISO 179              |
| Thermal                                  | Nominal Value | Unit     | Test Method          |
| Brittleness Temperature                  | -60.0         | °C       | ASTM D746A, ISO 974  |
| Vicat Softening Temperature              | 124           | °C       | ASTM D1525, ISO 306  |
| Peak Crystallization Temperature (DSC)   | 132           | °C       | ASTM D3418, ISO 3146 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

