

SUMIPLOY® FS2200

Polyethersulfone
Sumitomo Chemical Co., Ltd.

Message:

SUMIPLOY® FS2200 is a Polyethersulfone (PESU) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of SUMIPLOY® FS2200 are:

- Flame Rated
- Chemical Resistant
- Creep Resistant
- Flame Retardant
- Good Dimensional Stability

General Information			
UL YellowCard	E54705-100988654	E249884-100962054	
Additive	PTFE Lubricant (10%)		
Features	Flame Retardant		
	Gasoline Resistance		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Dimensional Stability		
	Good Impact Resistance		
	High ESCR (Stress Crack Resist.)		
	High Heat Resistance		
	Lubricated		
	Oil Resistant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.60	%	
Across Flow	0.60	%	
Water Absorption (24 hr)	0.39	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	77.0	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	2450	MPa	ASTM D790
Flexural Strength	118	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (6.40 mm)	78	J/m	ASTM D256
Unnotched Izod Impact (6.40 mm)	980	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	203	°C	ASTM D648
CLTE			ASTM D696
Flow : -50 to 150°C	5.9E-5	cm/cm/°C	
Transverse : 50 to 150°C	6.2E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Arc Resistance	80.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.430 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	340	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

