

DiaAlloy FE-30V

Polyphenylene Ether

Mitsubishi Rayon America Inc.

Message:

DiaAlloy FE-30V is a Polyphenylene Ether (PPE) material. It is available in North America.

Important attributes of DiaAlloy FE-30V are:

Flame Rated

Heat Resistant

Flame Retardant

Impact Resistant

Typical application of DiaAlloy FE-30V: Electrical/Electronic Applications

General Information			
Features	Flame Retardant		
	Good Heat Aging Resistance		
	Good Impact Resistance		
	High Heat Resistance		
Uses	Computer Components		
	Connectors		
UL File Number	E85500		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	49.0	MPa	ASTM D638
Tensile Elongation (Yield)	60	%	ASTM D638
Flexural Modulus	2450	MPa	ASTM D790
Flexural Strength (Yield)	93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	70	J/m	
-30°C	90	J/m	
23°C	210	J/m	
Unnotched Izod Impact			ASTM D256
-40°C	100	J/m	
23°C	280	J/m	

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	125	°C	
1.8 MPa, Unannealed	115	°C	
Vicat Softening Temperature	140	°C	ASTM D1525
Melting Temperature	260 to 310	°C	
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

