

TAROLOX 111 G4 DX03

Polyethylene Terephthalate

Taro Plast S.p.A.

Message:

PET glass fibre reinforced 20%, self extinguishing V0 without PBDE/PBDF, high temperature resistance, good flow, very good mechanical, thermal and electrical properties, low moisture absorption, good dimensional stability. Special grade for lampholders. Product must be dried before moulding.
Approved IMQ - EN 60238/96 - lampholders T210
Available: different colors

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Dimensional Stability		
	Good Electrical Properties		
	Good Flow		
	High Heat Resistance		
	Low Moisture Absorption		
	Self Extinguishing		
Uses	Lighting Fixtures		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.58 to 1.60	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.30 to 0.40	%	
Across Flow	0.80 to 1.0	%	
Water Absorption (23°C, 24 hr)	0.060	%	ASTM D570, ISO 62
Granule Humidity	< 0.030	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ASTM D638, ISO 527-2
Tensile Strength (Break)	120	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.5	%	ASTM D638, ISO 527-2
Flexural Modulus	7000	MPa	ASTM D790, ISO 178
Flexural Stress			
--	190	MPa	ISO 178
Break	190	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Charpy Unnotched Impact Strength ¹ (23°C)	35	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	60	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	230	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature ²	140	°C	IEC 60216
Vicat Softening Temperature	235	°C	ISO 306/B50, ASTM D1525 ³
Ball Pressure Test (245°C)	Pass		VDE 0470
Melting Temperature	256	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	2.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Comparative Tracking Index (Solution A)	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-1		
3.20 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
Oxygen Index	32	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	100 to 130	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	6x4x50mm		
2.	20000 hrs		
3.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT