

Osterlene® LD07520

Low Density Polyethylene

Osterman & Company

Message:

LD07520 is designed for a wide variety of industrial film applications where high impact strength and excellent drawdown are needed. LD07520 exhibits uniformity, ease of processing and good tensile strength.

Generally recommended extrusion conditions include a melt temperature range of 310°-350°F (155°-177°C) and a blow-up ratio range of 1.8-2.5:1.

Drawdown to gauges below 1.0 mils (<25 microns) is possible at commercial rates when proper techniques are used. Specific limitations may apply, contact your Osterman sales representative for more information.

Osterlene LD07520 meets the requirements of the Food and Drug Administration, 21 CFR Section 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations may apply. Contact your Osterman sales representative for more information.

General Information			
Features	Workability, good		
	Good strength		
Uses	Industrial application		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	46		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	10.7	MPa	ASTM D638
Fracture	11.4	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	100	%	ASTM D638
Fracture	700	%	ASTM D638
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM E111
1% secant, MD	179	MPa	ASTM E111
1% secant, TD	221	MPa	ASTM E111
Tensile Strength			ASTM D882
MD: Fracture	23.4	MPa	ASTM D882
TD: Fracture	16.5	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	160	%	ASTM D882
TD: Fracture	480	%	ASTM D882

Dart Drop Impact ¹	130	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	300	g	ASTM D1922
TD	180	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature ²	-75.0	°C	ASTM D746
Vicat Softening Temperature	90.0	°C	ASTM D1525
NOTE			
1.	F50		
2.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

