

Dialon 1015GF30

Polycarbonate

DTR S.r.l. (Develop Thermoplastic Resins)

Message:

Dialon 1015GF30 is a Polycarbonate (PC) material filled with 30% glass fiber. It is available in Europe. Primary attribute of Dialon 1015GF30: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Medium Flow		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	130	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	8000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	140	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/B50
Flammability	Nominal Value	Test Method	
Flame Rating (3.20 mm)	V-1	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT