

GERMADUR KSZ GF 30

Polybutylene Terephthalate
Kunststoff-Kontor-Hamburg GmbH

Message:

GERMADUR KSZ GF 30 is a Polybutylene Terephthalate (PBT) material filled with 30% glass fiber. It is available in Europe.
Important attributes of GERMADUR KSZ GF 30 are:
Flame Rated
Impact Modified
Impact Resistant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
	Low Temperature Impact Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8500	MPa	ISO 527-2
Tensile Stress (Yield)	130	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	16	kJ/m²	ISO 179
Charpy Unnotched Impact Strength	70	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	220	°C	ISO 75-2/B
Melting Temperature	225	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

