

KEBAFORM® C 25.0

Acetal (POM) Copolymer

BARLOG plastics GmbH

Message:

POM Copolymer unreinforced

General Information			
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	2.0	%	
Flow	2.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2640	MPa	ISO 527-2
Tensile Stress (Yield)	62.0	MPa	ISO 527-2
Tensile Strain (Yield)	9.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	110	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+18	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flammability Classification	HB		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

