

# Electroblend® PP-1900

Polypropylene Homopolymer

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

## Message:

Electroblend® PP-1900 is a low flow antistatic polypropylene compound characterized by superb impact strength properties.

General Information			
Additive	Antistatic		
Features	Antistatic		
	High Impact Resistance		
	Low Flow		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
	Industrial Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.2 to 1.4	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	28.0	MPa	ASTM D638
Tensile Elongation (Break)	55	%	ASTM D638
Flexural Modulus	1150	MPa	ASTM D790
Flexural Strength	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	500	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 4.00 mm)	98.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3 to 1.0E+5	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	185 to 190	°C	
Middle Temperature	190 to 195	°C	

Front Temperature	195 to 210	°C
Nozzle Temperature	210 to 220	°C
Processing (Melt) Temp	190 to 220	°C
Mold Temperature	60.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

