

MAJ'ECO EG150G - 1199

Biodegradable Polymers

AD majoris

Message:

MAJ'ECO EG150G-1199 is a biodegradable polymer (Biodeg Polymers) product. It can be processed by injection molding and is available in Europe. Features include:
flame retardant/rated flame
environmental protection/green

General Information			
Features	Updatable resources		
	Recyclable materials		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	10	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2/1
Tensile Stress (Break)	27.0	MPa	ISO 527-2/50
Flexural Modulus ¹	2370	MPa	ISO 178
Flexural Stress ²	52.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eU
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	140 - 180	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

