

ADEKA EP-4100TX

Epoxy; Epoxide
Adeka Corporation

Message:
Amorphous, low temperature curing
Civil engineering, coatings

General Information		
Features	Amorphous	
Uses	Coating Applications	
	Engineered Applications	
Physical	Nominal Value	Unit
Specific Gravity	1.16	g/cm ³
Chlorine Content - Saponifiable	1.9	wt%
Color - G, Max	1.0	
Epoxy Equivalent	210 g/ep	
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	13000	cP

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT