

Quadrant EPP Proteus® Black

Polypropylene Homopolymer

Quadrant Engineering Plastic Products

Message:

Quadrant EPP Proteus® Black is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in North America.

Characteristics include:

Flame Rated

Chemical Resistant

Homopolymer

General Information			
Features	Acid Resistant		
	Alcohol Resistant		
	Alkali Resistant		
	Homopolymer		
	Machinable		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	< 0.010	%	
Saturation	< 0.010	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1190	MPa	ASTM D638
Tensile Strength (Ultimate)	33.1	MPa	ASTM D638
Tensile Elongation (Break)	12	%	ASTM D638
Flexural Modulus	1240	MPa	ASTM D790
Flexural Strength (Yield)	33.1	MPa	ASTM D790
Compressive Modulus	1380	MPa	ASTM D695
Compressive Strength (10% Strain,23°C)	34.5	MPa	ASTM D695
Coefficient of Friction (vs. Steel - Static)	0.25		Internal Method
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	98.9	°C	ASTM D648
Maximum Use Temperature - Long Term, Air	82	°C	
Peak Crystallization Temperature (DSC)	160	°C	ASTM D3418

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.18 mm, Estimated Rating)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

