

RTP EMI 461.25 HI FR

High Impact Polystyrene

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
EMI/RFI Shielding - Stainless Steel Fiber 12.5% - High Impact - Flame Retardant

General Information			
Filler / Reinforcement	Stainless steel fiber, 13% filler by weight		
Features	Conductivity		
	Electromagnetic shielding (EMI)		
	Electrostatic discharge protection		
	Impact resistance, high		
	Radio frequency shielding (RFI)		
	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	26.2	MPa	ASTM D638
Tensile Elongation (Yield)	10	%	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength	46.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	87.8	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3	ohms	ASTM D257
Volume Resistivity	10	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Additional Information			
Surface Resistivity, ASTM D257: <1000 ohmSurface Resistivity, ESD S11.11: 10%Volume Resistivity, ASTM D257: <10 ohm-cm			

Injection	Nominal Value	Unit
Drying Temperature	82.2	°C
Drying Time	2.0	hr
Processing (Melt) Temp	204 - 246	°C
Mold Temperature	65.6 - 82.2	°C
Injection Pressure	68.9 - 103	MPa

Injection instructions

Remove hopper magnets. Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

