

LNP™ THERMOCOMP™ JF004Z compound

Polyethersulfone

SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP JF004Z is a compound based on Polyethersulfone resin containing Glass Fiber. Added features of this material include: HV.

Also known as: LNP* THERMOCOMP* Compound JF-1004 EHV

Product reorder name: JF004Z

General Information			
Filler / Reinforcement	Glass Fiber		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.25 to 0.45	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6700	MPa	ISO 527-2/1
Tensile Stress (Break)	120	MPa	ISO 527-2/5
Tensile Strain (Break)	2.7	%	ISO 527-2/5
Flexural Modulus ²	5800	MPa	ISO 178
Flexural Stress	178	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	40	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, Unannealed, 64.0 mm Span	225	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	221	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	360 to 371	°C	
Front Temperature	371 to 382	°C	
Processing (Melt) Temp	354 to 371	°C	
Mold Temperature	138 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	Tensile Bar		

2.	2.0 mm/min
3.	80*10*4
4.	80*10*4
5.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

