

Delrin® 327UVE RD402

ACETAL RESIN
DuPont Performance Polymers

Message:
UV Stabilized Medium-high Viscosity Acetal Homopolymer with Very Low Emissions

General Information			
Additive	Mold Release		
	UV Stabilizer		
Forms	Pellets		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>POM<		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2
Tensile Stress (Yield)	72.5	MPa	ISO 527-2
Tensile Strain (Yield)	20	%	ISO 527-2
Nominal Tensile Strain at Break	40	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	92.0	°C	ISO 75-2/A
Melting Temperature ¹	178	°C	ISO 11357-3
Additional Information	Nominal Value	Unit	Test Method
Emission	< 2.00	mg/kg	VDA 275
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

