

Larton L K/20

Polyphenylene Sulfide

LATI S.p.A.

Message:

Compound based on Linear Polyphenylene Sulphide (L-PPS).

Carbon fibre.

Very good chemical resistance. Very good thermal resistance. Low smoke toxicity index and optical density.

General Information			
Filler / Reinforcement	Carbon Fiber,20% Filler by Weight		
Features	Good Chemical Resistance		
	High Heat Resistance		
	Low Optical Density		
	Low Smoke Emission		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.20 to 0.30	%	
Flow : 2.00 mm	0.10 to 0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	18000	MPa	
60°C	16000	MPa	
90°C	12500	MPa	
120°C	9200	MPa	
150°C	7500	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	145	MPa	
Break, 60°C	125	MPa	
Break, 90°C	95.0	MPa	
Break, 120°C	65.0	MPa	
Break, 150°C	45.0	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	1.0	%	
Break, 60°C	1.2	%	
Break, 90°C	1.5	%	
Break, 120°C	1.9	%	
Break, 150°C	2.1	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA

Charpy Unnotched Impact Strength (23°C)	18	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	35	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	280	°C	ISO 75-2/B
1.8 MPa, Unannealed	270	°C	ISO 75-2/A
Continuous Use Temperature ²	200	°C	
Vicat Softening Temperature	255	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	4.0E-6	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+3	ohms	ASTM D257
Volume Resistivity	8.0E+3	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	290 to 310	°C	
Mold Temperature	130 to 140	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT