# SILVER® FC-1

### Polyvinyl Chloride

Guangdong Silver Age Sci & Tech. Co., Ltd

#### Message:

SILVER® PVC for Injection Molding conforming ROHS and DEHP is applied to power connector plugs and other injection molding parts for electrical appliance. In addition, the custom—made products should be developed by buyers 'requirements in order to meet special usage.

General Information			
Uses	Appliances		
	Connectors		
	Electrical/Electronic Applications		
	Plugs		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	
Specific Gravity	1.45	g/cm³	
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	6.0	g/10 min	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore A)	85		
Mechanical	Nominal Value	Unit	
Tensile Strength <sup>1</sup>	14.5	MPa	
Tensile Elongation (Break)	140	%	
Thermal	Nominal Value	Unit	
Brittleness Temperature	-30.0	°C	
Flammability	Nominal Value		Test Method
Flame Rating	V-2		UL 94
Additional Information	Nominal Value	Unit	
Volatile Loss	< 20.0	g/m²	
NOTE			
1.	after aging		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

