

Lucon® PO6062

Polyphenylene Ether + PS

LG Chem Ltd.

Message:

Lucon® PO-6062 is a Polyphenylene Ether + PS (PPE+PS) material filled with carbon fiber, carbon nano and glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Lucon® PO-6062 are:

ESD Protection

Heat Resistant

High Strength

Typical application of Lucon® PO-6062: Electrical/Electronic Applications

General Information			
Filler / Reinforcement	Carbon Fiber		
	Carbon Nano		
	Glass Fiber		
Features	ESD Protection		
	Good Thermal Stability		
	High Strength		
Uses	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	167	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	8.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	9810	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	235	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	195	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4 to 1.0E+6	ohms	IEC 60093
Injection	Nominal Value	Unit	Test Method
Drying Temperature	90.0 to 110	°C	
Drying Time	4.0 to 5.0	hr	

Rear Temperature	270 to 290	°C
Middle Temperature	280 to 300	°C
Front Temperature	280 to 310	°C
Nozzle Temperature	280 to 300	°C
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	90.0 to 120	°C
Back Pressure	0.00 to 0.981	MPa
Screw Speed	40 to 60	rpm

NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	15 mm/min	
4.	15 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT