

# AVP™ RLL30CP

Polycarbonate  
SABIC Innovative Plastics

Message:

AVP™ RLL30CP is a Polycarbonate (PC) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America. Applications of AVP™ RLL30CP include electrical/electronic applications, appliances and automotive. Characteristics include:  
Eco-Friendly/Green  
Good Toughness  
High Strength  
Rigid

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Recycled Content	Yes		
Features	Good Toughness		
	High Rigidity		
	High Strength		
Uses	Appliance Components		
	Automotive Applications		
	Communication Applications		
	Electrical Parts		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 3.18 mm)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8270	MPa	ASTM D638
Tensile Strength (Yield)	131	MPa	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	7240	MPa	ASTM D790
Flexural Strength (Yield)	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	143	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Drying Time, Maximum	16	hr	
Rear Temperature	282 to 304	°C	
Middle Temperature	293 to 316	°C	
Front Temperature	304 to 338	°C	
Nozzle Temperature	304 to 338	°C	
Processing (Melt) Temp	316 to 343	°C	
Mold Temperature	82.2 to 116	°C	
Back Pressure	0.345 to 1.38	MPa	
Screw Speed	60 to 80	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

