

BONDYRAM® 4108

Linear Low Density Polyethylene

Polyram Ram-On Industries

Message:

Maleic Anhydride Modified Linear Low Density Polyethylene Recommended as coupling agent for PE composites filled with high filler content for Halogen Free Flame Retarded cables composites.

General Information			
Features	Flame Retardant		
	Halogen Free		
Uses	Wire & Cable Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238, ISO 1133
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	124	°C	ASTM D3417, ISO 11357-3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

