

LNP™ THERMOCOMP™ PX01658 compound

Polyamide 6

SABIC Innovative Plastics

Message:

LNP THERMOCOMP PX01658 is a compound based on Nylon 6 containing Proprietary Fillers.

Also known as: LNP* THERMOCOMP* Compound PDX-P-01658

Product reorder name: PX01658

General Information			
Filler / Reinforcement	Proprietary		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.10 to 0.30	%	
Across Flow : 24 hr	0.50 to 0.70	%	
Water Absorption			
24 hr, 50% RH	0.75	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	32700	MPa	ASTM D638
--	30900	MPa	ISO 527-2/1
Tensile Strength			
Break ²	257	MPa	ASTM D638
Break	267	MPa	ISO 527-2/5
Tensile Strain			
Yield	2.0	%	ISO 527-2/5
Break ³	2.0	%	ASTM D638
Break	1.9	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	24700	MPa	ASTM D790
-- ⁵	25800	MPa	ISO 178
Flexural Stress			
--	393	MPa	ISO 178
Yield, 50.0 mm Span ⁶	392	MPa	ASTM D790
Break, 50.0 mm Span ⁷	391	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	120	J/m	ASTM D256
23°C ⁸	11	kJ/m ²	ISO 180/1A

Unnotched Izod Impact			
23°C	1000	J/m	ASTM D4812
23°C ⁹	68	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	13.0	J	ASTM D3763
--	3.70	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	220	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁰	220	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	213	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	210	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	1.9E-5	cm/cm/°C	
Transverse : -30 to 30°C	6.4E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	266 to 277	°C	
Front Temperature	277 to 288	°C	
Processing (Melt) Temp	266 to 277	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	1.3 mm/min		
8.	80*10*4		
9.	80*10*4		
10.	80*10*4 mm		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

