

Ravamid® A T BK

Polyamide 66

Ravago Group

Message:

Black, elastomer modified, medium impact
All the products are also available Heat Stabilized (H) and UV Stabilized (UV)

General Information			
Additive	Impact Modifier		
Recycled Content	Yes		
Features	Impact Modified		
	Medium Impact Resistance		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm³	ASTM D792, ISO 1183
Molding Shrinkage - Flow	1.2 to 1.7	%	ASTM D955
Humidity	< 0.25	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638, ISO 527-2
Yield	40.0	MPa	
Break	38.0	MPa	
Tensile Elongation (Break)	23	%	ASTM D638, ISO 527-2
Flexural Modulus	1900	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	10.0	kJ/m²	ASTM D256
Notched Izod Impact Strength (23°C)	10	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	65.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	210	°C	ISO 306/B50, ASTM D1525 1
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

