

Ravaflex EPDM

Ethylene Propylene Diene Terpolymer

Ravago Group

Message:

Reprocessed terpolymer of ethylene, propylene and diene with a very good processibility

General Information			
Features	Antioxidation		
	Workability, good		
	Terpolymer		
Appearance	White		
	Grey		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.860 - 0.870	g/cm ³	ASTM D297
Mooney Viscosity (ML 1+4, 125°C)	30 - 80	MU	ASTM D1646
Ethylene Content	50.0 - 70.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	2.5 - 6.5	wt%	ASTM D6047
Antioxidant Additive	Nonstaining		
Moisture Content (105°C)		%	Internal method
Ash content-1 hr (550°C)		%	ASTM D297
	1000		
Packaging	510000	g	
Additional Information	Nominal Value	Unit	

It is compatible for co-curing with conventional diene rubbers. It shows an excellent resistance to oxidative and ozone degradation.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT