

MAJORIS GFR307 - 8229

Polypropylene

AD majoris

Message:

MAJORIS GFR307 - 8229 is a special long glass fibre reinforced polypropylene compound halogen free flame retardant UL 94 VO classification, for injection moulding and extrusion. The long glass fibres, chemically coupled to the polypropylene matrix, are providing with outstanding mechanical properties. This quality is UV stabilised.

MAJORIS GFR307 - 8229 is available both in natural (MAJORIS GFR307) and black (MAJORIS GFR307-8229). Other colours can be provided on request.

APPLICATIONS

MAJORIS GFR307 - 8229 is intended for injection moulding of highly demanding technical applications.

The excellent properties of MAJORIS GFR307 - 8229 make it suitable for:

Electrical components, structural furniture parts, load bearing, demanding components for various engineering sectors.

MAJORIS GFR307 - 8229 can, in many of these applications, substitute other engineering plastics or metal alloys.

| General Information | | | |
|-----------------------------|-----------------------|-------------------|-----------------|
| Filler / Reinforcement | Long glass fiber | | |
| Additive | heat stabilizer | | |
| | UV stabilizer | | |
| | Flame retardancy | | |
| Features | Chemical coupling | | |
| | Good UV resistance | | |
| | Recyclable materials | | |
| | Heat resistance, high | | |
| | Thermal Stability | | |
| | Halogen-free | | |
| | Flame retardancy | | |
| Uses | Electrical components | | |
| | Furniture | | |
| | Metal substitution | | |
| Appearance | Black | | |
| | Available colors | | |
| | Natural color | | |
| Forms | Particle | | |
| Processing Method | Extrusion | | |
| | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.15 | g/cm ³ | ISO 1183 |
| Molding Shrinkage (2.00 mm) | 0.60 | % | Internal method |

| Mechanical | Nominal Value | Unit | Test Method |
|--|---------------|-------------------|----------------|
| Tensile Modulus | 6700 | MPa | ISO 527-2/1 |
| Tensile Stress (Break) | 80.0 | MPa | ISO 527-2/50 |
| Tensile Strain (Break) | 3.0 | % | ISO 527-2/50 |
| Flexural Modulus ¹ | 7300 | MPa | ISO 178 |
| Flexural Stress | 150 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 14 | kJ/m ² | ISO 179/1eA |
| Charpy Unnotched Impact Strength (23°C) | 30 | kJ/m ² | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature | | | |
| 0.45 MPa, not annealed | 156 | °C | ISO 75-2/B |
| 1.8 MPa, not annealed | 143 | °C | ISO 75-2/A |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating (1.60 mm) | V-0 | | UL 94 |
| Glow Wire Flammability Index (1.00 mm) | 960 | °C | IEC 60695-2-12 |
| Glow Wire Ignition Temperature (2.00 mm) | 825 | °C | IEC 60695-2-13 |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 180 - 220 | °C | |
| Processing (Melt) Temp | 180 - 220 | °C | |
| Mold Temperature | 60.0 - 100 | °C | |
| Injection Pressure | 30.0 - 60.0 | MPa | |
| Injection Rate | Slow | | |
| Screw Speed | 30 - 150 | rpm | |
| Injection instructions | | | |
| Holding pressure: 50 to 70% of the injection pressureBack pressure: as low as possible, 0 to 10%Holding time: as long as practical | | | |
| NOTE | | | |
| 1. | 2.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT