

ALTECH® ABS A 1000/906

Acrylonitrile Butadiene Styrene

ALBIS PLASTIC GmbH

Message:

ALTECH® ABS A 1000/906 is an acrylonitrile butadiene styrene (ABS) product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALTECH®The application areas of ABS A 1000/906 include houses and tools.

Features include:

Comply with REACH standard

ROHS certification

beautiful

General Information			
Features	Excellent appearance		
Uses	Power/other tools		
	Shell		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	19.0	cm³/10min	ISO 1133
Molding Shrinkage (24 hr)	0.40 - 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress (Yield)	45.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	2.6	%	ISO 527-2
Fracture	10	%	ISO 527-2
Flexural Stress	65.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	22	kJ/m²	ISO 179/1eA
-30°C	8.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
--	170	kJ/m²	ISO 179/1eU
-30°C	130	kJ/m²	ISO 179/1eU
Notched Izod Impact (23°C)	25	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	92.0	°C	ISO 75-2/B

1.8 MPa, not annealed	80.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	105	°C	ISO 306/A50
--	96.0	°C	ISO 306/B50
Thermal Conductivity ¹	0.20	W/m/K	ISO 22007-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Dehumidification desiccant	80	°C	
Hot air dryer	80	°C	
Drying Time			
Dehumidification desiccant	3.0 - 6.0	hr	
Hot air dryer	2.0 - 4.0	hr	
Processing (Melt) Temp	220 - 260	°C	
Mold Temperature	50 - 80	°C	
NOTE			
1.	Integral		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

