

TORZEN Marathon™ G4000XHL BK20

Polyamide 66
INVISTA Engineering Polymers

Message:

TORZEN Marathon™ G4000XHL BK20 is a 40% glass reinforced, heat stabilized, black, PA66 resin with a significantly improved balance of continuous heat and peak temperature property retention, along with higher flow and similar shrinkage compared to conventional PA66 resins

General Information	
Filler / Reinforcement	Glass Fiber,40% Filler by Weight
Additive	Heat Stabilizer
Features	Good Mold Release
	Heat Stabilized
	High Flow
Agency Ratings	EC 1907/2006 (REACH)
RoHS Compliance	RoHS Compliant
Appearance	Black
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.47	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	0.85 to 0.95	%	
Flow : 2.00 mm	0.35 to 0.45	%	
Water Absorption			ISO 62
23°C, 24 hr	0.70	%	
Equilibrium, 23°C, 50% RH	1.1	%	

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12300	MPa	ISO 527-2
Tensile Stress (Break)	225	MPa	ISO 527-2
Tensile Strain (Break)	2.8	%	ISO 527-2
Flexural Modulus	12000	MPa	ISO 178
Flexural Stress	330	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	11	kJ/m²	
23°C	13	kJ/m²	
Notched Izod Impact Strength (23°C)	13	kJ/m²	ISO 180

Thermal	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Heat Deflection Temperature			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ISO 75-2/A
Melting Temperature	262	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.080 to 0.18	%	
Rear Temperature	250 to 270	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	50.0 to 90.0	°C	
Back Pressure	0.200 to 1.00	MPa	
Cushion	4.00 to 6.00	mm	
Vent Depth	7.0E-3 to 0.040	mm	
Screw Speed	Low rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

