

Sarlink® TPV X5735B

Thermoplastic Vulcanizate

Teknor Apex Company

Message:

Sarlink® TPV X5735B is a Thermoplastic Vulcanizate (TPV) material. It is available in Asia Pacific, Europe, Latin America, or North America.

Typical application of Sarlink® TPV X5735B: Automotive

General Information			
Appearance	Opaque		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.928	g/cm ³	ASTM D792
--	0.930	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240, ISO 868
Shore A, 5 sec, Extruded	34		
Shore A, 5 sec, Injection Molded	36		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 37
Across Flow : 100% Strain	0.800	MPa	
Flow : 100% Strain	1.70	MPa	
Tensile Strength			ASTM D412, ISO 37
Across Flow : Break	3.30	MPa	
Flow : Break	2.60	MPa	
Tensile Elongation			ASTM D412, ISO 37
Across Flow : Break	530	%	
Flow : Break	210	%	
Tear Strength - Across Flow			
--	9.98	kN/m	ASTM D624
-- ¹	10	kN/m	ISO 34-1
Compression Set			ASTM D395, ISO 815
23°C, 22 hr	12	%	
70°C, 22 hr	23	%	
125°C, 70 hr	42	%	
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			
135°C, 1000 hr	-5.0	%	ASTM D573, ISO 188
100% Strain, 135°C, 1000 hr	4.0	%	ASTM D573
150°C, 168 hr	2.0	%	ASTM D573, ISO 188
100% Strain, 150°C, 168 hr	8.0	%	ASTM D573

100% Strain 135°C, 1000 hr	4.0	%	ISO 188
100% Strain 150°C, 168 hr	8.0	%	ISO 188
Change in Ultimate Elongation in Air - Across Flow			ASTM D573, ISO 188
135°C, 1000 hr	15	%	
150°C, 168 hr	12	%	
Change in Durometer Hardness in Air			ASTM D573, ISO 188
Shore A, 135°C, 1000 hr	0.0		
Shore A, 150°C, 168 hr	1.0		
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	110	%	ASTM D471, ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	210	Pa·s	ISO 11443
200°C	210	Pa·s	ASTM D3835
NOTE			

1. Method Ba, Angle (Unnicked)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT