

PRL PC-G30

Polycarbonate

Polymer Resources Ltd.

Message:

PRL PC-G30 is a Polycarbonate (PC) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

RoHS Compliant

Flame Retardant

Heat Resistant

General Information			
UL YellowCard	E113219-219244		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
	High Heat Resistance		
	Self Extinguishing		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.0 to 12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.10 to 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	124	MPa	
Break, 3.18 mm	124	MPa	
Flexural Modulus (3.18 mm)	6890	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	152	°C	
1.8 MPa, Unannealed, 3.18 mm	146	°C	
RTI Elec			UL 746
1.70 mm	80.0	°C	
3.00 mm	80.0	°C	
RTI Imp			UL 746

1.70 mm	80.0	°C
3.00 mm	80.0	°C
RTI Str		UL 746
1.70 mm	80.0	°C
3.00 mm	80.0	°C
Flammability	Nominal Value	Test Method
Flame Rating		UL 94
1.70 mm	V-2	
3.00 mm	V-0	
Injection	Nominal Value	Unit
Drying Temperature	118 to 124	°C
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	293 to 316	°C
Middle Temperature	304 to 327	°C
Front Temperature	316 to 338	°C
Processing (Melt) Temp	302 to 329	°C
Mold Temperature	82.2 to 116	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

