

TRANSMARE® 10HGF30-0.001

Polypropylene Homopolymer

Transmare Compounding B.V.

Message:

TRANSMARE® 10HGF30-0.001 is a 30% chemically coupled glass fiber reinforced polypropylene homopolymer. It combines good impact properties with a high stiffness, and good flow properties.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Chemically Coupled		
	Good Flow		
	Good Impact Resistance		
	High Stiffness		
	Homopolymer		
	Recyclable Material		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	76		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (4.00 mm)	6500	MPa	ISO 527-2/1
Tensile Stress (Break, 4.00 mm)	90.0	MPa	ISO 527-2/50
Tensile Strain (Break, 4.00 mm)	3.0	%	ISO 527-2/50
Flexural Modulus	5460	MPa	ISO 178
Flexural Stress	126	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1A
-40°C	6.5	kJ/m ²	
23°C	8.6	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1U
-40°C	38	kJ/m ²	
23°C	47	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	7.7	kJ/m ²	
23°C	11	kJ/m ²	

Unnotched Izod Impact Strength			ISO 180/1U
-40°C	41	kJ/m ²	
23°C	45	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	156	°C	ISO 75-2/B
1.8 MPa, Unannealed	127	°C	ISO 75-2/A
Vicat Softening Temperature	163	°C	ISO 306/A
Additional Information	Nominal Value	Unit	Test Method
Emission - of Volatile Organics ¹	< 50.0(fulfilled)	µgC/g	Internal Method
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.20	%	
Rear Temperature	170	°C	
Middle Temperature	230	°C	
Front Temperature	240	°C	
Nozzle Temperature	250	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Slow-Moderate		
NOTE			
1.	VW 50180, PV 3341		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT