

Badamid® A70 GF30 L H

Polyamide 66

Bada AG

Message:

Badamid® A70 GF30 L H is a polyamide 66 (nylon 66) material, which contains a 30% glass fiber reinforced material. This product is available in Europe.
Badamid® The main characteristics of A70 GF30 L H are: flame retardant/rated flame.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Forms		Particle		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.34	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturated, 23°C	5.5	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.8	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9000	6500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	165	125	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.5	5.0	%	ISO 527-2/5
Flexural Stress (23°C)	210	170	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	16	16	kJ/m ²	ISO 179/1eA
23°C	17	24	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	85	90	kJ/m ²	ISO 179/1eU
23°C	95	100	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	16	15	kJ/m ²	ISO 180/1A
23°C	17	23	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ¹				
0.45 MPa, not annealed	250	--	°C	ISO 75-2/B
1.8 MPa, not annealed	235	--	°C	ISO 75-2/A
Melting Temperature (DSC)	262	--	°C	ISO 3146
Linear thermal expansion coefficient				ISO 11359-2
Flow: 4.00mm	3.0E-5	--	cm/cm/°C	ISO 11359-2

Lateral: 4.00mm	6.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Dielectric Constant (1 MHz)	3.50	5.40		IEC 60250
Dissipation Factor (1 MHz)	0.014	0.16		IEC 60250
Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
Additional Information				
干燥				
Short-Term Heat Resistance, IEC 216, 20000 hrs: 220°CLong-Term Heat Resistance, IEC 216, 50% decrease of yield stress: 115°C				
Injection	Dry	Unit		
Processing (Melt) Temp	280 - 300		°C	
Mold Temperature	80.0 - 110		°C	
NOTE				
1.	110x10x4mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

