

MARPOL® Homo 12.NA

Polypropylene Homopolymer

Marco Polo International, Inc.

Message:

Additives: Nucleation and Antistat
Recommended Applications: Caps, closures, and thin wall containers
Homo 12.NA has passed USP Class VI testing, an all ingredients meet the chemical registration requirements of TSCA (U.S.) and DSL (Canada). Homo 12.NA complies with all applicable FDA regulations for food contact applications.

General Information			
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Food Contact Acceptable		
	Homopolymer		
	Nucleated		
Uses	Caps		
	Closures		
	Thin-walled Containers		
Agency Ratings	FDA Food Contact, Unspecified Rating		
	USP Class VI		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (A-Scale)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1720	MPa	ASTM D638
Tensile Strength (Yield)	37.2	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus	1590	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	27	J/m	ASTM D256A
Unnotched Izod Impact (23°C)	850	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	127	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT